



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 19/01/2018**

**TO: 24/01/2019**

LAB. ID NUMBER: 41837  
POWDER COATING: DS-0857S  
HEAT TRANSFER FILM: 2507/19  
Colour variation ( $\Delta E$ ): **0,14**  
residual gloss: **93%**

### **Technical Remarks**

Excellent residual gloss and normal colour variation ( $\Delta E$ ).

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

