

 **Florida
Test**

 **Total duration:
12 months**

 **EXPOSURE PERIOD:**

FROM: 21/11/2019

TO: 11/01/2021

LAB. ID NUMBER: 46187
POWDER COATING: 9G-242-A009
HEAT TRANSFER FILM: 6064/02
colour variation (ΔE): 1,70
residual gloss: 84%

Technical Remarks

Excellent residual gloss and normal colour variation (ΔE)

Technical Opinion:
Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS
The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

