



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **20/04/2015**

TO: **09/05/2016**

LAB. ID NUMBER: 36807
POWDER COATING: DS-0733S
HEAT TRANSFER FILM: 1806/02
Colour variation (ΔE): **1,16**
residual gloss: **98%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

Unexposed area
(reference)

Exposed
area

