

 **Florida
Test**

 **Total duration:
12 months**

 **EXPOSURE PERIOD:**

FROM: 13/10/2016

TO: 20/10/2017

LAB. ID NUMBER: 40580
POWDER COATING: DS 797
HEAT TRANSFER FILM: 1836/01
Colour variation (ΔE): **1,14**
residual gloss: **76%**

Technical Remarks

Good residual gloss and low colour variation (ΔE).

Technical Opinion:
Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS
The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

