



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 07/08/2012**

**TO: 106/08/2013**

LAB. ID NUMBER: 22443  
POWDER COATING: DS 1716  
HEAT TRANSFER FILM: 2502/01  
colour variation ( $\Delta E$ ): **2,02**  
residual gloss: 85%

**Technical Remarks**

Good residual gloss and low colour variation ( $\Delta E$ )

Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye.

**Unexposed area  
(reference)**

**Exposed  
area**

