



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **20/08/2013**

TO: **21/08/2014**

LAB. ID NUMBER: 32049
POWDER COATING: Mirror-107S
HEAT TRANSFER FILM: 5026/02
Colour variation (ΔE): **1,63**
residual gloss: **100%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

Unexposed area
(reference)

Exposed
area

