



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 21/09/2021

TO: 20/10/2022

LAB. ID NUMBER: 50841
POWDER COATING: DS 704
HEAT TRANSFER FILM: 2505/10
Colour variation (ΔE): 0,96
residual gloss: 66%

Technical Remarks

Good residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

