



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 05/10/2012

TO: 04/10/2013

LAB. ID NUMBER: 25917
POWDER COATING: DS-0804S
HEAT TRANSFER FILM: 5001/02
Colour variation (ΔE): 1,07
residual gloss: 90%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

