



**Florida  
Test**



**Total duration:  
12 month**



**EXPOSURE PERIOD:**

**FROM: 18/08/2011**

**TO: 30/08/2012**

LAB. ID NUMBER: 24603  
POWDER COATING: DS 457  
HEAT TRANSFER FILM: 6001/01L  
colour variation ( $\Delta E$ ): 0,55  
residual gloss: 128%

**Technical Remarks**

Excellent residual gloss and very low colour variation  
( $\Delta E$ )

Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

