



Florida  
Test



Total duration:  
12 months



EXPOSURE PERIOD:

FROM: **23/05/2014**

TO: **27/05/2015**

LAB. ID NUMBER: 34079  
POWDER COATING: DS-1716S  
HEAT TRANSFER FILM: 1401/01  
Colour variation ( $\Delta E$ ): **2,12**  
residual gloss: **100%**

### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ ).


### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).



Unexposed area  
(reference)

Exposed  
area

