





Florida Test



Total duration: 12 months



EXPOSURE PERIOD:

FROM: 31/07/2023

> TO: 22/08/2024

LAB. ID NUMBER: 54611 POWDER COATING: DS-0803S HEAT TRANSFER FILM: 1448/20 Colour variation (ΔE): **1,34** residual gloss: 96%

Technical Remarks

Excellent residual gloss and normal colour variation (ΔE) .


Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye



Date: 19/06/2025