



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 10/08/2022**

**TO: 10/08/2023**

LAB. ID NUMBER: 50779  
POWDER COATING: 9C-016-A001  
HEAT TRANSFER FILM: 2602/08  
colour variation ( $\Delta E$ ): 0,54  
residual gloss: 83%

**Technical Remarks**

Good residual gloss and low color variation ( $\Delta E$ )

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

