



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 30/04/2009**

**TO: 28/04/2010**

LAB. ID NUMBER: 17539  
POWDER COATING: DS-0721S  
HEAT TRANSFER FILM: 2601/01L  
colour variation ( $\Delta E$ ): **0,98**  
residual gloss: **108%**

**Technical Remarks**

Excellent residual gloss and very low colour variation  
( $\Delta E$ )

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area  
(reference)**

**Exposed  
area**

