



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **04/06/2020**

TO: **04/06/2021**

LAB. ID NUMBER: 47005
POWDER COATING: Deep Matt-008
HEAT TRANSFER FILM: 1413/03
Colour variation (ΔE): 1,05
residual gloss: 83%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

