



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 04/06/2020

TO: 04/06/2021

LAB. ID NUMBER: 47012
POWDER COATING: Subliwallsky-733
HEAT TRANSFER FILM: 2501/02
Grey scale: 4/5
residual gloss: 90%

Technical Remarks

Excellent residual gloss and low colour variation.

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

