



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 10/08/2022

TO: 10/08/2023

LAB. ID NUMBER: 50775
POWDER COATING: 9C-301-A004
HEAT TRANSFER FILM: 6052/01
colour variation (ΔE): 1,85
residual gloss: 96%

Technical Remarks

Excellent residual gloss and normal color variation
(ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with
the naked eye

**Unexposed area
(reference)**

**Exposed
area**

