

 **Florida  
Test**

 **Total duration:  
12 months**

 **EXPOSURE PERIOD:**

**FROM: 20/12/2012**

**TO: 02/01/2014**

LAB. ID NUMBER: 28328  
POWDER COATING: DS 403  
HEAT TRANSFER FILM: 1002/01  
Colour variation ( $\Delta E$ ): **1,36**  
residual gloss: **91%**

**Technical Remarks**

Excllent residual gloss and low colour variation ( $\Delta E$ ).

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALICOAT REQUIREMENTS**

The residual gloss shall be at least 50% of the original gloss.  
The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

