



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **18/08/2016**

TO: **18/08/2017**

LAB. ID NUMBER: 40221
POWDER COATING: Mirror-188S
HEAT TRANSFER FILM: 1505/01
Colour variation (ΔE): **0,63**
residual gloss: **100%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

Unexposed area
(reference)

Exposed
area

