



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 10/08/2022

TO: 10/08/2023

LAB. ID NUMBER: 50252
POWDER COATING: DS 439L
HEAT TRANSFER FILM: 1806/06
colour variation (ΔE): **2,84**
residual gloss: **78%**

Technical Remarks

Good residual gloss and normal color variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

