



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 31/07/2023

TO: 22/08/2024

LAB. ID NUMBER: 54542
POWDER COATING: DS 402
HEAT TRANSFER FILM: 1401/19
Colour variation (ΔE): **3,61**
residual gloss: **51%**

Technical Remarks

Residual gloss is sufficient, but colour variation is very high so not acceptable for outdoor use.

Technical opinion:

Not for outdoor use

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eyes.

**Unexposed area
(reference)**

**Exposed
area**

