



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 12/08/2010

TO: 17/08/2011

LAB. ID NUMBER: 22430
POWDER COATING: DS 716
HEAT TRANSFER FILM: 1301/03L
colour variation (ΔE): **2,43**
residual gloss: **59%**

Technical Remarks

Good residual gloss and very low colour variation
(ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

