



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 31/07/2023

TO: 22/08/2024

LAB. ID NUMBER: 55099
POWDER COATING: DS-0745S
HEAT TRANSFER FILM: 2901/10
Colour variation (ΔE): 2,05
residual gloss: 79%

Technical Remarks

Residual gloss is good, but colour variation is very high so not acceptable for outdoor use.

Technical opinion:

Not for outdoor use

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eyes.

**Unexposed area
(reference)**

**Exposed
area**

