



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 04/06/2020

TO: 04/06/2021

LAB. ID NUMBER: 47011
POWDER COATING: Subliwallsky-739
HEAT TRANSFER FILM: 2301/02
Grey scale: 4
residual gloss: 52%

Technical Remarks

Sufficient residual gloss and normal colour variation.

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

