



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 07/08/2012**

**TO: 06/08/2013**

LAB. ID NUMBER: 27414  
POWDER COATING: DS 402  
HEAT TRANSFER FILM: 1602/01  
Colour variation ( $\Delta E$ ): 1,8  
residual gloss: 94%

**Technical Remarks**

Excllent residual gloss and low colour variation ( $\Delta E$ ).

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALICOAT REQUIREMENTS**

The residual gloss shall be at least 50% of the original gloss.

The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).



**Unexposed area  
(reference)**

**Exposed  
area**

