



**EXPOSURE PERIOD:**

**FROM: 27/11/2015**

**TO: 19/12/2016**

LAB. ID NUMBER: 38511  
POWDER COATING: Subliwallsky-733  
HEAT TRANSFER FILM: 1403/02  
Colour variation ( $\Delta E$ ): 1,55  
residual gloss: 86%

**Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ )

**Technical Opinion:**  
**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALICOAT REQUIREMENTS**  
The residual gloss shall be at least 50% of the original gloss.  
The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

