



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 07/08/2012

TO: 06/08/2013

LAB. ID NUMBER: 27450
POWDER COATING: DS 402
HEAT TRANSFER FILM: 2511/05
Colour variation (ΔE): **1,97**
residual gloss: **94%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.
The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

