



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 31/07/2023**

**TO: 22/08/2024**

LAB. ID NUMBER: 54533  
POWDER COATING: DS 401  
HEAT TRANSFER FILM: 2305/17  
Colour variation ( $\Delta E$ ): **2,52**  
residual gloss: **66%**

### **Technical Remarks**

Good residual gloss and normal colour variation ( $\Delta E$ ).

### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

### **REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

