



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 14/01/2012

TO: 16/01/2013

LAB. ID NUMBER: 25677
POWDER COATING: MirrorL-183S
HEAT TRANSFER FILM: 6047/15L
colour variation (ΔE): 1
residual gloss: 105%

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

