

 **Florida
Test**

 **Total duration:
12 months**

 **EXPOSURE PERIOD:**

FROM: 10/08/2022

TO: 10/08/2023

LAB. ID NUMBER: 52579
POWDER COATING: DS 733
HEAT TRANSFER FILM: 2505/02
colour variation (ΔE): 1,33
residual gloss: 74%

Technical Remarks

Good residual gloss and normal color variation (ΔE)

Technical Opinion:
Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS
The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

