



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 10/08/2022

TO: 10/08/2023

LAB. ID NUMBER: 46210
POWDER COATING: Mirror-030S
HEAT TRANSFER FILM: 5014/12
colour variation (ΔE): **0,42**
residual gloss: **100%**

Technical Remarks

Excellent residual gloss and low color variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

