



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 27/11/2015**

**TO: 19/12/2016**

LAB. ID NUMBER: 38443  
POWDER COATING: DS 1704M  
HEAT TRANSFER FILM: 2501/15  
Colour variation ( $\Delta E$ ): 0,3  
residual gloss: 75%

**Technical Remarks**

Good residual gloss and low colour variation ( $\Delta E$ )

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**QUALICOAT REQUIREMENTS**

The residual gloss shall be at least 50% of the original gloss.

The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

