

 **Florida
Test**

 **Total duration:
12 months**

 **EXPOSURE PERIOD:**

FROM: 01/05/2021

TO: 01/05/2022

LAB. ID NUMBER: 49994
POWDER COATING: 8G-933-A002
HEAT TRANSFER FILM: 1424/03
colour variation (ΔE): 2,95
residual gloss: 68%

Technical Remarks

Sufficient residual gloss and normal colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

