



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 23/05/2022

TO: 27/05/2023

LAB. ID NUMBER: 55469
POWDER COATING: DS-1739M12U
HEAT TRANSFER FILM: 2301/02
Colour variation (ΔE): **1,73**
residual gloss: **78%**

Technical Remarks

Good residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

