



Florida  
Test



Total duration:  
12 months



EXPOSURE PERIOD:

FROM: 27/11/2015

TO: 19/12/2016

LAB. ID NUMBER: 38590  
POWDER COATING: DS 733  
HEAT TRANSFER FILM: 1811/18  
Colour variation ( $\Delta E$ ): 2,03  
residual gloss: 94%

### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ )

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).



Unexposed area  
(reference)

Exposed  
area

