



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 23/02/2020**

**TO: 27/02/2021**

LAB. ID NUMBER: 52521  
POWDER COATING: DS 716  
HEAT TRANSFER FILM: 5024/01  
Colour variation ( $\Delta E$ ): **1,98**  
residual gloss: **84%**

**Technical Remarks**

Good residual gloss and normal colour variation ( $\Delta E$ ).

Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye

**Unexposed area  
(reference)**

**Exposed  
area**

