



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 12/08/2010**

**TO: 17/08/2011**

LAB. ID NUMBER: 22441  
POWDER COATING: DS 716  
HEAT TRANSFER FILM: 2106/02L  
colour variation ( $\Delta E$ ): 3,66  
residual gloss: 60%

#### **Technical Remarks**

Residual gloss is very low and colour variation is very high so not acceptable for outdoor use.

Technical opinion:

**Not for outdoor use**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

