



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 20/12/2012

TO: 02/01/2014

LAB. ID NUMBER: 28561
POWDER COATING: DS 733
HEAT TRANSFER FILM: 2530/03
Colour variation (ΔE): **2,11**
residual gloss: **71%**

Technical Remarks

Good residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

**Unexposed area
(reference)**

**Exposed
area**

