



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 13/10/2016**

**TO: 20/10/2017**

LAB. ID NUMBER: 40509  
POWDER COATING: DS 775  
HEAT TRANSFER FILM: 2305/17  
Colour variation ( $\Delta E$ ): **0,98**  
residual gloss: **82%**

### **Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ ).

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

