



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 13/07/2005

TO: 13/07/2006

LAB. ID NUMBER: 7797
POWDER COATING: DS 402
HEAT TRANSFER FILM: 2104/01L
colour variation (ΔE): 0,98
residual gloss: 83%

Technical Remarks

Excellent residual gloss and very low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

