



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 25/11/2013

TO: 25/11/2014

LAB. ID NUMBER: 32811
POWDER COATING: 9G-036-A004
HEAT TRANSFER FILM: 6048/02
Grey Scale: 4
residual gloss: 79%

Technical Remarks

Good residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area
(reference)**

**Exposed
area**

