



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 13/07/2005

TO: 13/07/2006

LAB. ID NUMBER: 7798
POWDER COATING: DS 402
HEAT TRANSFER FILM: 2301/01L
colour variation (ΔE): 2,75
residual gloss: 81%

Technical Remarks

Residual gloss is excellent but colour variation is very high so not acceptable for outdoor use.

Technical opinion:

Not for outdoor use

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

