



EXPOSURE PERIOD:

FROM: 27/11/2015

TO: 19/12/2016

LAB. ID NUMBER: 38370
POWDER COATING: DS 421
HEAT TRANSFER FILM: 2301/02
Colour variation (ΔE): 1,77
residual gloss: 90%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE)

Technical Opinion:
Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS
The residual gloss shall be at least 50% of the original gloss.
The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

