



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 14/01/2012**

**TO: 14/01/2013**

LAB. ID NUMBER: 25653  
POWDER COATING: DS 725  
HEAT TRANSFER FILM: 2801/02  
Colour variation ( $\Delta E$ ): **2,31**  
residual gloss: **98%**

### **Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ ).

### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area  
(reference)**

**Exposed  
area**

