



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 27/11/2015

TO: 19/12/2016

LAB. ID NUMBER: 38456
POWDER COATING: DS-0703IMS
HEAT TRANSFER FILM: 2001/03
Colour variation (ΔE): **2,08**
residual gloss: **94%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

**Unexposed area
(reference)**

**Exposed
area**

