



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 23/05/2014

TO: 27/05/2015

LAB. ID NUMBER: 53788
POWDER COATING: DS-0733S
HEAT TRANSFER FILM: 1401/01
Colour variation (ΔE): **1,43**
residual gloss: 93%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).


Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye.



**Unexposed area
(reference)**

**Exposed
area**

