



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 13/01/2011**

**TO: 17/01/2012**

LAB. ID NUMBER: 23552  
POWDER COATING: Mirror 22  
HEAT TRANSFER FILM: 6006/13M  
colour variation ( $\Delta E$ ): 5,54  
residual gloss: 77%

### **Technical Remarks**

Excellent residual gloss and very low colour variation ( $\Delta E$ )

### Technical Opinion:

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALIDECO REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

