



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 05/10/2012

TO: 04/10/2013

LAB. ID NUMBER: 25921
POWDER COATING: Mirror-030
HEAT TRANSFER FILM: 2502/12
Colour variation (ΔE): **1,59**
residual gloss: **100%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALIDECO REQUIREMENTS

The residual gloss must be at least 50% of the original gloss. The final evaluation will be based on visual inspection with the naked eye, with a maximum value of 4 on the grey scale (ISO 105-A02).

**Unexposed area
(reference)**

**Exposed
area**

