



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 27/11/2015**

**TO: 19/12/2016**

LAB. ID NUMBER: 38477  
POWDER COATING: DS-0739S  
HEAT TRANSFER FILM: 1405/02  
Colour variation ( $\Delta E$ ): **1,03**  
residual gloss: **100%**

#### **Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ )

#### **Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

#### **QUALICOAT REQUIREMENTS**

The residual gloss shall be at least 50% of the original gloss.

The  $\Delta E$  values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

**Unexposed area  
(reference)**

**Exposed  
area**

