



**Florida  
Test**



**Total duration:  
12 months**



**EXPOSURE PERIOD:**

**FROM: 13/07/2005**

**TO: 13/07/2006**

LAB. ID NUMBER: 53790  
POWDER COATING: DS-0716S  
HEAT TRANSFER FILM: 1501/02  
Colour variation ( $\Delta E$ ): **1,12**  
residual gloss: **95%**

**Technical Remarks**

Excellent residual gloss and low colour variation ( $\Delta E$ ).

**Technical Opinion:**

**Suitable for OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

**REQUIREMENTS**

The residual gloss must be at least 50% of the original gloss.  
The final evaluation will be based on visual inspection with the naked eye.

**Unexposed area  
(reference)**

**Exposed  
area**

