



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: 27/11/2015

TO: 19/12/2016

LAB. ID NUMBER: 38421
POWDER COATING: DS 726
HEAT TRANSFER FILM: 1829/02
Colour variation (ΔE): 5,73
residual gloss: 59%

Technical Remarks

Residual gloss is sufficient but colour variation is very high so not acceptable for outdoor use.

Technical opinion:

Not for outdoor use

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

REQUIREMENTS

The residual gloss must be at least 50% of the original gloss.
The final evaluation will be based on visual inspection with the naked eye

